

## Environmental Product Declaration

**Reinforcing Bar and Mesh** 

Programme operator:

and EN 15804+A1

EPD registration number: Date of publication (issue): Date of revision: Valid until:

In accordance with ISO 14025

EPD Australasia www.epd-australasia.com S-P-00858 Version 1.2 2016-11-08 2022-05-20 2025-09-21

mmm





#### ARC - The Australian Reinforcing Company

The Australian Reinforcing Company (ARC) is a leading manufacturer and supplier of steel reinforcing in Australia.



Produced under EPD Australasia by thinkstep-anz in accordance with ISO 14025 and EN 15804+A1

EPD registration number S-P-00858 Version 1.2 Publication date Version date Valid until Geographical scope

2016-11-08 2022-05-20 2025-09-21 Australia

### **General information**

An Environmental Product Declaration, or EPD, is a standardised and verified way of quantifying the environmental impacts of a product based on a consistent set of rules known as PCR (Product Category Rules).

| Declaration<br>owner: InfraBuild  |   | InfraBuild Australia Pty Ltd           Web:         www.infrabuild.com           Email         sustainablesteel@infrabuild.com  |  |  |
|---|---|---|--|--|
| EPD<br>produced<br>by:  | thinkstep   | thinkstep Pty Ltd         Web:       www.thinkstep-anz.com         Email:       info@thinkstep-anz.com         Post:       616 Harris Street, Ultimo, New South Wales 2007, Australia |  |  |
| EPD<br>Programme<br>Operator:   | AUSTRALASIA EPD®<br>ENVIRONMENTAL PRODUCT DECLARATION | EPD Australasia Ltd         Web:       www.epd-australasia.com         Email:       info@epd-australasia.com         Post:       315a Hardy Street, Nelson 7010, New Zealand          |  |  |
| CEN standard  | I EN 15804 served as the co                           | re PCR:   |  |  |
| PCR:  |   | PCR 2012:01 Construction products and Construction services,<br>Version 2.31, 2019-12-20  |  |  |
| PCR review was conducted by:  |   | The Technical Committee of the International EPD® System  |  |  |
| Chair:  |   | Massimo Marino. Contact via info@environdec.com   |  |  |
| Independent verification of the declaration and data, according to ISO 14025: |   | <ul> <li>EPD process certification (Internal)</li> <li>EPD verification (External)</li> </ul>   |  |  |
| Third<br>party<br>verifier:   |   | Rob Rouwette (start2see Pty Ltd)<br>Email: Rob.Rouwette@start2see.com.au  |  |  |
| Verifier accree<br>or approved b  |   | EPD Australasia Ltd   |  |  |

| Version | Date and Description  |
|---------|---|
| 1       | November 2016 – Original EPD released.  |
| 1.1     | September 2020 – Updated in line with 5-year validity, including updated hotspot data covering over 95% of all impacts. |
| 1.2     | May 2022 – Update InfraBuild branding. Update ARC address details on back cover.  |

S-P-00858 Version 1.2

ARC



## Contents

| General information                            | 2  |
|--|----|
| Table of contents                              | 3  |
| Welcome  | 4  |
| How to use this EPD                            | 5  |
| Benefits of using this EPD                     | 6  |
| Benefits of using ARC products                 | 7  |
| Reinforcing Bar and Mesh products              | 8  |
| Steelmaking processes                          | 9  |
| The Material Circularity Indicator / ISO 14001 | 11 |
| Technical information                          | 13 |
| Reinforcing Bar                                | 16 |
| Reinforcing Mesh                               | 18 |
| Acronyms                                       | 20 |
| References                                     | 21 |



### Welcome

The Australian Reinforcing Company (ARC) is one of the leading manufacturers and suppliers of steel reinforcing in Australia.

Our aim is to make it safe, fast and simple for our suppliers and customers to partner with us. Whether it's one of our state manufacturing facilities or your local ARC branch, we have a network of sites across Australia to supply all your reinforcing needs.

We're a true blue Australian company with a history that mirrors the history of this country since 1920. ARC steel is in the bones of everything from your front driveway to the iconic landmarks that symbolise Australia to the rest of the world.

As an organisation we are committed to sustainability. Sustainability goes far beyond establishing a company recycling program, or turning off the lights when everyone goes home. We have a vision to meet the economic, environmental and social needs of our employees and customers, while preserving the opportunity for future generations to do the same. We strive for continual improvement of environmental performance, by producing more with less of the earth's resources and the minimisation of pollution at world's best practice rates.

Our Australian-made steel is sourced from InfraBuild's steel mills in Newcastle and Rooty Hill in NSW and Laverton in Victoria, and from Liberty Primary Steel in Whyalla, SA.

ARC's Environmental Product Declaration (EPD) is independently verified and is a premier contributor to our holistic commitment to the environmentally sustainable manufacture and application of our products.

Recognising our customers' needs and the increasing demand for standardisation and greater transparency around environmental performance, ARC is proud to publish the sustainability credentials of our supply chain and products.

ARC is part of the InfraBuild national steel supply chain. InfraBuild has stated its ambition to become carbon neutral by 2030, and its superior product quality and technical expertise position it as a partner to Australia's construction industry.

Its core competencies in metallurgy, steel manufacture, supply chain, logistics, expert consultation and information management, support you in building Australia's future.

ARC is dedicated to conducting its business to global environmental, social and commercial standards. This commitment to the environment includes optimising the eco-efficiency of its products through the product life cycle. This means improving resource and energy efficiencies in the production and distribution of its products, and during the use of steel products. ARC is committed to the promotion of the recovery, reuse and recycling of steel and other products.

#### The major changes in this EPD include:

- Update InfraBuild branding
- · Update ARC address details on back cover.

#### www.arcreo.com.au





### How to use this EPD

ARC recognises the importance of the transparency and independent verification of our products' credentials. This Environmental Product Declaration (EPD) covers the environmental impacts of reinforcing bar and mesh.

Reinforcing bar and mesh are manufactured to AS/NZS 4671 *Steel* reinforcing materials.

Our products manufactured to AS/NZS 4671 are third-party certified by the Australasian Certification Authority for Reinforcing and Structural Steels (ACRS) to independently confirm they consistently meet the requirements of the Standard.

These products are typically used in the construction industry.

### **General guidance**

EPDs are independently verified documents that include information about the environmental impact of products throughout their life cycle.

EPDs require the completion of Life Cycle Inventory (LCI), a Life Cycle Assessment (LCA) and verification to best practice international and Australian standards.

- Life Cycle Inventory (LCI) is the collection of data on the inputs, processes and outputs within a defined system boundary
- Life Cycle Assessment (LCA) is the modelling of LCI in accordance with ISO 14040 and ISO 14044 standards
- Third party verification of the output of the LCA in the format of an EPD.

The EPD owner has the sole ownership, liability and responsibility for the EPD.

## EPDs are not always comparable

When comparing EPDs it is important to recognise:

- EPDs within the same product category from different programmes may not be comparable
- EPDs of construction products may not be comparable if they do not comply with EN 15804 or if they are produced using different Product Category Rules
- EPDs of construction products from a group of manufacturers may not be comparable to an EPD of a similar construction product that has been generated by a single manufacturer.

Understanding the detail is important in comparisons. Expert analysis is required to ensure data is truly comparable to avoid unintended distortions.



### **Benefits of using this EPD**

- Provides an independently verified representation of the environmental impact of ARC product going into your project.
- Complies with the requirements of a valid EPD that is recognised in the Green Star Design & As Built v1.3 and Innovation Challenge of Green Star legacy tools by the Green Building Council of Australia (GBCA).
- Complies with the requirements of IS® rating tool by the Infrastructure Sustainability Council (ISC).

Green Building Council Australia

#### **Green Star® Points**

This EPD complies with requirements under the Green Building Council of Australia's rating tool, Green Star – Design & As Built v1.3.

Green Star points for EPDs can be claimed under the Sustainable Products credit when the following criteria are met:

- ✓ EN 15804 and ISO 14025 compliant
- ✓ Verified by an independent third party
- ✓ Cradle-to-gate scope.

This EPD meets these requirements.



#### IS Tool®

This EPD complies with requirements under the Infrastructure Sustainability Council's IS® rating scheme:

- ✓ Compliant with ISO 14025
- ✓ Compliant with EN15804
- ✓ Verified by a third party.

This EPD may help your project achieve ISv2.0 Rso-7 or ISv1.2 Mat-2 credits under the

IS® rating scheme.

#### **ISC ISupply**

ISC's ISupply Directory connects sustainable products and services with projects and assets undertaking an IS rating.

InfraBuild has been part of the ISupply Directory since its inception. Our listing within the ISupply directory can help your project or asset achieve sustainability outcomes rewarded under the IS rating scheme.

www.isupply.org.au/listing/structural-steel-reinforcing-bar-and-mesh-pre-stressing-strandand-rail-products/

ARC





### **Benefits of using ARC products**

#### Why steel?

#### Steel is fundamental to the way we live, work and play.

As one of the most utilised materials in the world, steel supports the buildings we use, strengthens the roads and bridges that connect us and contributes to a more sustainable built environment.

From design and construction, through to building and infrastructure use, and then at the end of the asset lifespan, steel offers construction proponents unique sustainability benefits.

Steel can be readily adapted for various uses. It allows asset owners to modify existing structures to cater for future uses and tenants, as well as extending the structure's lifespan beyond its initial intent.

Steel is a 100% recyclable material, with no loss in material strength or quality.

Modern design techniques and the use of higher strength grades can also reduce the mass of steel used in structures.

To understand the environmental performance of steel, the full life cycle of steel must be taken into consideration. The key steps in the life cycle of steel are shown in Figure 1 (page 8).


#### Why ARC?

#### At ARC, we understand that sustainability is not just about environmental impact.

We strive to improve our social licence to operate across social, economic and environmental arenas while upholding our core values of Family, Change and Sustainability.

For more information refer to www.arcreo.com.au





### **Reinforcing Bar and Mesh products**

This EPD includes data on two products: reinforcing bar and reinforcing mesh.

Each of the products included in this EPD are available in a wide range of sizes. A detailed description of the products can be found on pages 16 and 18.

Under the United Nations Central Product Classification (UN CPC), ARC's reinforcing bar and mesh products fall into three categories:

- 41241: Bars and rods, hot rolled, in irregularly wound coils, of iron and non-alloy steel
- 41242: Other bars and rods of iron or non-alloy steel, not further worked than forged, hot rolled, hot drawn or hot extruded, but including those twisted after rolling
- 41264: Bars and rods, cold formed or cold finished, of alloy steel.

Under the Australian and New Zealand Standard Industrial Classification (ANZSIC), the products within this EPD are described by the following Class Code and Title;

• 2221 Structural Steel Fabrication

ARC operates across Australia supplying qualitycontrolled steel reinforcing products to all levels of the construction industry. The latest in scheduling technology is used to provide an incredibly accurate take-off, saving costs and wastage. Reinforcing bar and mesh are cut and bent to Australian Standards to suit the particular needs of the customer. Our specialist prefab centres are capable of manufacturing a vast range of prefabricated reinforcing elements as required.

The ARC delivery service can transport all of your reinforcing and accessories to site safely and without fuss. Alternatively, product for smaller jobs can be easily and safely picked up at one of our drive-though metropolitan branches.

This EPD relates to products manufactured by ARC and does not included imported products or components. The production process is conceptually hereafter in Figure 3 (page 10).



# Steelmaking processes

ARC uses steel produced using two different, but complementary, manufacturing processes.

The first involves InfraBuild's Electric Arc Furnaces (EAF), which primarily use scrap steel and electricity.

The second uses Liberty Primary Steel's integrated steel mill at Whyalla, SA, which incorporates key unit processes such as coke manufacture, Blast Furnace (BF) and Basic Oxygen Steelmaking (BOS). This process primarily uses raw materials such as coal and iron ore.

These processes are complementary because EAF steelmaking cannot occur without scrap steel feed that has previously been created through the integrated steel manufacturing process.

The interdependency of the two processes is recognised by rating tools including Green Star® and IS® in that steel from both processes can contribute equally to obtaining credits under schemes.


Manufacturers and designers alike play a key role in improving the sustainability credentials of steel and steel structures.

Designers are encouraged to select the most suitable steel for an application to maximise the efficiency of the design and thus reduce the quantities consumed. As a manufacturer, InfraBuild works to provide products and services that are increasingly sustainable. These include higher strength steel solutions that have the capacity to reduce the amount of steel consumed.





Figure 2: The typical composition of ARC's reinforcing bar and mesh




A range of alloys are used to manufacture the products and grades represented in this EPD. The use of alloys has been aggregated and averaged in this EPD. The impact of utilising alloys to produce different grades or products has no material impact on the outcome of this EPD.

Products have been grouped such that the variations between the EPD outcomes for individual sections within the same product grouping are deemed as not significant to the EPD result. The upstream manufacturing processes are common across the various products represented within a product group.

The products included in this EPD do not contain any substances of high concern as defined by European REACH regulation.

Figure 3: Reinforcing bar and mesh products manufactured by ARC



ARC



### **The Material Circularity Indicator**

The Circular Economy is a system that requires us to reconsider the entire lifecycle of our products and resources by designing out waste. That means making use of materials and technologies that extend the lifespan and potential reuse value of the things we produce, while minimising as far as possible unintended waste and pollutants.


With that, there remains a need to quantify this process so producers can know just how circular their products are. The Material Circularity Indicator (MCI) not only provides a benchmark for improving a product but can add extra value to an EPD, providing a more complete picture of the overall sustainability credentials of that product.

EPDs go a long way towards establishing a product's overall environmental impact by looking at the entire lifecycle of a product via an internationally standardised approach and independent verification. However on their own, EPDs stop short of quantifying a Circular Economy approach. This is where the MCI can help to offer a more complete picture and ensure that circular economy steps are well underway.

The Ellen McArthur Foundation, building on their strong work publicising the Circular Economy, developed the MCI to measure the circularity of products. The indicator's focus is on Technical Cycles, "in which products, components and materials are kept in the market at the highest possible quality and for as long as possible, through repair and maintenance, reuse, refurbishment, remanufacture, and ultimately recycling". (Ellen McArthur Foundation 2015)

With this, we can see that the MCI is particularly relevant to organisations working in building and infrastructure areas and encouraging more circular design principles from the extraction of raw resources, to the construction and eventual demolition stages.

This process is demonstrated in Figure 4 below, with the MCI tracking material flows from virgin stock, to use and eventual reuse. In short, its focus is entirely on the materials going in and the waste coming out along each step of a product's lifecycle. It also considers a product's utility when making the calculation, which includes the intensity of use and intended lifespan. Finally, the MCI has a simple scale of 0–1, with 0.1 indicating a linear process and 1 indicating a fully circular one. A result of less than 0.1 indicates a linear product with lower-than-average utility.



#### Figure 4: Diagrammatic representation of Material Flows (Ellen McArthur Foundation 2015)



#### What this looks like in practice

As part of the development of this EPD, thinkstep-anz were commissioned to develop an MCI for the products in this EPD.

For the Reinforcing Bar products (page 16), their MCI score of 0.696 shows a good level of circularity, reflecting a high proportion of recycled steel input as well as their recyclability potential at end of life.

For the Reinforcing Mesh products (page 19), their MCI score of 0.581 shows these products are moving towards greater circularity, reflecting their recycled steel content as well as their recyclability potential at end of life.

Increased use of the MCI as a metric for infrastructure projects will help the industry to improve resource efficiency across the whole life of a project. InfraBuild is playing its part by transparently providing MCI results in all EPDs.

In a broader sense, and in line with the objectives of the MCI according to the Ellen McArthur Foundation, this MCI provides InfraBuild with important information to add to its growing sustainability picture. Although this MCI only applies to one of many products, it is nonetheless vital information as production shifts from a linear model to a circular one.

### **ISO** 14001

ISO 14001 is the international standard that specifies requirements for an effective Environmental Management System (EMS) that help organisations administer and control a company's environmental impact and compliance with regulations.

Although it is a voluntary standard that organisations can certify to, the GBCA Green Star Design & As Built tool uses ISO 14001 as one criteria to define a 'Responsible Steel Maker'.

This requirement states: "The steel making facilities where the structural and/or reinforcing steel for the project is sourced have a currently valid and certified ISO 14001 Environmental Management System (EMS) in place. Valid ISO 14001 Environmental Management System (EMS) certificates must be provided from the steel making facilities where the structural and/or reinforcing steels in the project were produced."

InfraBuild has ISO 14001 EMS certification and the current certificate is available via the following link:

www.infrabuild.com/en-au/resource-centre/resources/iso14001-cem20182-environmental-management-system





### **Technical information**

#### Declared Unit

This EPD is valid for a declared unit of one tonne (t) of product ready for dispatch to a customer.

#### System boundaries

The system boundary of this EPD includes stages A1-A3, C3-C4 and D as shown in Table 1. This scope is referred to as 'cradle-to-gate with options'.

The production phase of this EPD includes mining of raw materials, transport to, between and within the different manufacturing sites, and manufacturing of semi-finished steel followed by rolling and forming into the final product at the exit gate.

When a structure reaches its end-of-life, the majority of the steel used in the structure is recovered and scrapped for recycling (C3). A recycling rate of 90% has been applied for this EPD (National Waste Report 2018). The remaining 10% is assumed to be landfilled (C4).

Module D considers the environmental impact and benefit of steel recycling in its second life cycle.

Information contained in this EPD excludes the use phase environmental impacts of the product, which are considered to be too variable to provide meaningful representation.


#### Benefits and Construction Product loads beyond process Use stage End-of-life stage stage the system stage boundary Transport to waste processing Deconstruction / demolition Transport of raw materials Construction / Installation Operational energy use Operational water use Transport to customer Raw material supply Waste processing Manufacturing Refurbishment Replacement Maintenance Recycling. Recovery Disposal ootential Reuse-Repair Jse C3 A1 A2 A5 B1 B2 B3 Β4 B5 B6 B7 C1 C2 C4 D A3 A4 Х Х Х MND Х Х Х X = included in the EPD; MND = module not declared (such a declaration shall not be regarded as an indicator result of zero).

#### Table 1: Modules included in the scope of the EPD

#### Life cycle inventory (LCI) data

The Life Cycle Inventory data used in this EPD has been collected and applied according to EN 15804:2012+A1:2013, ISO 14025 and PCR 2012:01 Construction Products and Construction Services v2.31 (2019-12-20) of the International EPD® System.





### **Key assumptions**

#### Data for core processes:

Primary (specific) data was collected for all inputs and outputs from ARC sites in the production stage (A1–A3). Direct emissions measured based on the Australian National Pollutant Inventory (NPI) scheme were provided by

ARC for all steel manufacturing sites. Specific information on waste water composition and discharges were provided by ARC for processes likely to contaminate the water and therefore require treatment.

The original version of this EPD (2016) was based on an annual average for the time period July 2013 to June 2014. This EPD is based on an annual average for the time period July 2018 to June 2019, for all hotspots covering all inputs with a combined contribution of more than 95% of all main EN15804 impact categories.

#### Data for upstream and downstream processes:

Secondary (generic) data was used for all raw materials, energy and transport processes, as allowed under the PCR (IEPDS 2019). All data is from the GaBi Life Cycle Inventory Database 2020 and is typically representative of the years 2016 to 2019, depending on the dataset (Sphera 2020). Australian data was used where possible. Where regional data was unavailable, average data or data from other regions was used.

#### Data for credit and burden:

Our own processes for production of virgin steel and recycled steel have been used to calculate the credit or burden for the net recycling of scrap in Module D. This differs from the approach taken in 2014, which used global average data provided by worldsteel.

#### Electricity mixes:

Electricity consumption was modelled using statespecific grid mixes. The background data for the electricity sources (such as coal, wind power, etc.) is based on background data from the GaBi Life Cycle Inventory Database 2020 (Sphera 2020). Electricity consumption accounts for a significant proportion of total energy sources for the EAF processes. The SA grid mix (Whyalla) is 42% natural gas, 33% wind, and 24% imported from VIC, with a carbon intensity of 792 g  $CO_2e/kWh$ . The NSW grid mix (Sydney EAF) is predominantly hard coal (77%) with, 3.3% natural gas, 4.1% hydro, 2.5% wind, 6.5% imported from VIC, and 5.6% imported from QLD, and has a carbon intensity of 1,020 g  $CO_2e/kWh$ . The VIC grid mix (Laverton EAF) is predominantly lignite (80%) with 6.3% wind, 6.3% hydro, 3.2% natural gas, 2.4% imported from TAS, and 1.1% import from NSW, and has a carbon intensity of 1,320 g  $CO_2e/kWh$ .

#### **Recycling:**

When a structure reaches its end-of-life, the majority of the steel used in the structure is recovered. The recycling rate was based on a report on the waste industry prepared for the Australian Government, which indicates an average recycling rate of 90% for metals in Australia. (National Waste Report 2018). The remaining 10% is assumed to be lost to landfill (C4).

#### Allocation:

Where required, co-product allocation using the most relevant physical quantity (mass, volume or energy) was applied for core processes. Economic allocation was applied, using annual average prices for the time period July 2018 to June 2019, where the differences in the price of the co-products was large (>25%), including lead waste, zinc dross, and mill scale.

Secondary material inputs (e.g. steel scrap and tyres) reach end-of-waste state at the entry gate to a recycling facility. The recycling process is included within the system boundary, but the inputs are treated as burden free.

No allocation is applied to EAF and BOS slag produced by the steel works, which are managed on site to reach end-of-waste state and either used in site construction works or given away at no cost to a third party. Allocation rules for secondary data (upstream/ downstream processes) are documented on the GaBi website (Sphera 2020). Recycling allocation follows the polluter pays principle in line with EN 15804 and the PCR.

#### Cut off criteria:

Environmental impacts relating to personnel, infrastructure, and production equipment not directly consumed in the process are excluded from the system boundary as per the PCR (IEPDS 2019). The only inputs knowingly excluded from the inventory are packaging materials for minor inputs such as alloys, greases, etc., which are used in very small quantities.

ARC



### **Environmental impact indicators**

EN 15804 and PCR 2012:01 v2.31 require the environmental indicators below, calculated based on CML characterisation factors (as updated in 2012).

#### Table 2: Environmental indicators based on CML characterisation factors

| Impact category<br>[Abbreviation]                      | Unit                      | Description   |  |
|--|---------------------------|---|--|
| Global warming<br>(climate change)<br>potential [GWP]  | kg $\rm{CO}_2$ equivalent | Potential of greenhouse gases – such as carbon dioxide – to increase absorption of heat reaching Earth's atmosphere, intensifying the natural greenhouse effect.  |  |
| Stratospheric ozone depletion potential [ODP]          | kg CFC 11 equivalent      | Potential of emissions that contribute to the reduction of the stratospheric ozone layer.   |  |
| Acidification potential of land and water [AP]         | kg $SO_2$ equivalent      | Potential of emissions to cause acidifying effects in the environment, typically due to acid rain. Potential downstream effects include fish mortality, forest decline and the deterioration of building materials.                               |  |
| Eutrophication<br>potential [EP]                       | kg $PO_4^{3}$ equivalent  | Potential of emissions – such as nitrogen and phosphorus – to increase nutrient levels in both aquatic and terrestrial ecosystems, which can cause undesirable shifts in species composition and elevated biomass production (e.g. algal blooms). |  |
| Photochemical ozone<br>creation potential<br>[POCP]    | kg $C_2H_4$ equivalent    | Potential of emissions to contribute to air pollution (ground-level smog - mainly ozone), which can be harmful to human and ecosystem health and can also damage crops.   |  |
| Depletion of abiotic<br>resources (elements)<br>[ADPE] | kg Sb equivalent          | Decrease of the availability of non-renewable material resources.   |  |
| Depletion of abiotic re-<br>sources (fossil) [ADPF]    | MJ net calorific value    | Decrease of the availability of non-renewable fossil fuel resources.  |  |

The following impact categories have been added to comply with the 'Additional Life Cycle Impact Reporting' requirement listed in the 'Green Star – Design and As Built' (2014) rating tool from the Green Building Council of Australia.

#### Table 3: Impact categories added to comply with the 'Additional Life Cycle Impact Reporting' requirement

| Impact category<br>[Abbreviation]      | Unit                    | Description  | Methodology   |
|--|-------------------------|--|---|
| Human toxicity, cancer<br>[HTPc]       | CTUh                    | Toxic effects of chemical emissions on human health due to cancer effects.                                       | USEtox (Rosenbaum et al. (2008))                      |
| Human toxicity, non-<br>cancer [HTPnc] | CTUh                    | Toxic effects of chemical emissions on human health due to non-cancer effects.                                   | USEtox (Rosenbaum et al. (2008))                      |
| Land use [LU]                          | kg C deficit            | Degradation of soil quality and fertility using Soil Organic Carbon as a proxy for Soil Organic Matter.          | SOM model (Milà i Canals,<br>Romanyà, & Cowell, 2006) |
| Resource depletion -<br>water [RDW]    | $m^3 H_2O$ equivalent   | Consumption of fresh water related to local and global water scarcity.   | Water Stress Indicator*<br>(Ridoutt & Pfister (2012)) |
| Ionising radiation [IR]                | kBq U-235<br>equivalent | Radioactive substances released<br>to the environment that can be<br>damaging to human health and<br>ecosystems. | Human health impacts<br>(Frischknecht et al. (2000))  |
| Particulate matter [PM]                | kg PM2.5 equivalent     | Contribution to air pollution which can have respiratory effects.  | Riskpoll (Rabi and Spadaro (2004))                    |

\*Using catchment specific characterisation factors from ALCAS http://auslci.com.au/Documents/WaterCatchmentswithnames.png.



### **Reinforcing Bar**

#### **Product description**

Reinforcing bar is a hot rolled deformed bar of normal ductility grade 500 steel that meets AS/NZS 4671 *Steel Reinforcing Materials.* It is produced in both straight lengths and coils in sizes from 10mm to 40mm diameter. The required strength is achieved through either quenching and self-tempering, the addition of alloying elements, or mechanical stressing (continuous stretching).

| Product         | Size range (mm)         | Section |
|-----------------|-------------------------|---------|
| Reinforcing Bar | 10 mm to 50 mm diameter |         |

#### Changes in results from previous EPD

GWP, ADPF, AP and EP have decreased due to an increased proportion of production from EAF and EAF efficiency improvements. POCP impacts have increased significantly due to increases in carbon monoxide, nitrogen oxides and sulphur dioxide emissions at Whyalla BOS. ADPE impacts have increased due to increases in alloy quantities used at Whyalla BOS, partly due to changes in steel chemistry and partly due to improved data collection. ODP has decreased by three orders of magnitude, due to updates in the background data sets reflecting the phase out of ozone depleting substances.

### **Results of assessment**

#### **Environmental impact indicators**

The following indicators describe potential environmental impacts for each product per declared unit.

| Indicator                                     | Production<br>A1 – A3 | Waste processing<br>C3 | Disposal<br>C4 | Recycling potential<br>D |
|---|-----------------------|------------------------|----------------|--------------------------|
| GWP [kg CO <sub>2</sub> -eq.]                 | 1.67E+03              | 2.60E+00               | 4.51E+00       | -7.99E+01                |
| ODP [kg CFC11-eq.]                            | 2.08E-12              | 1.51E-14               | 1.46E-14       | -1.86E-14                |
| AP [kg SO <sub>2</sub> -eq.]                  | 5.16E+00              | 1.72E-02               | 1.27E-02       | -7.16E-02                |
| EP [kg PO <sub>4</sub> <sup>3-</sup> -eq.]    | 5.56E-01              | 4.22E-03               | 1.35E-03       | -1.26E-02                |
| POCP* [kg C <sub>2</sub> H <sub>4</sub> -eq.] | 9.61E-01              | 1.89E-03               | 1.18E-03       | -9.49E-02                |
| ADPE [kg Sb-eq.]                              | 4.40E-04              | 2.93E-06               | 3.39E-07       | -3.51E-05                |
| ADPF [MJ]                                     | 1.86E+04              | 4.92E+01               | 6.85E+01       | -8.19E+02                |

Table 4: Potential environmental impacts, 1 tonne of reinforcing bar

The results from the impact assessment are only relative statements which give no information about the endpoint of the impact categories, exceeding of threshold values, safety margins or risk.

\*POCP values are slightly reduced due to nitrogen monoxide (NO) having a negative characterisation factor in the CML-IA methodology (Guinée et. al., 2002) implemented within EN 15804:2012+A1:2013. It should not be interpreted as NO reducing summer smog. This dampening effect present because the GaBi Databases used in this project (Sphera, 2020) split NO<sub>x</sub> emissions into NO and NO<sub>2</sub> for both mobile and stationary fuel combustion. POCP would be slightly higher if these emissions were instead grouped together as NO<sub>x</sub>. Extra care should be taken when comparing POCP values between EPDs.



#### **Resource indicators**

The following indicators describe the use of renewable and non-renewable material resources, renewable and non-renewable primary energy and water.

| Indicator            | Production<br>A1 – A3 | Waste processing<br>C3 | Disposal<br>C4 | Recycling potential<br>D |
|----------------------|-----------------------|------------------------|----------------|--------------------------|
| PERE [MJ]            | 1.05E+03              | 4.22E+00               | 4.94E+00       | -2.69E+01                |
| PERM [MJ]            | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |
| PERT [MJ]            | 1.05E+03              | 4.22E+00               | 4.94E+00       | -2.69E+01                |
| PENRE [MJ]           | 1.87E+04              | 5.02E+01               | 7.06E+01       | -8.22E+02                |
| PENRM [MJ]           | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |
| PENRT [MJ]           | 1.87E+04              | 5.02E+01               | 7.06E+01       | -8.22E+02                |
| SM [kg]              | 9.55E+02              | 0.00E+00               | 0.00E+00       | INA                      |
| RSF [MJ]             | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |
| NRSF [MJ]            | 6.20E+01              | 0.00E+00               | 0.00E+00       | 2.83E+00                 |
| FW [m <sup>3</sup> ] | 6.90E+00              | 1.31E-02               | 9.43E-04       | -9.25E-02                |

#### Wastes and other outputs

Table 6: Waste categories, 1 tonne of reinforcing bar

| Indicator | Production<br>A1 – A3 | Waste processing<br>C3 | Disposal<br>C4 | Recycling potential<br>D |
|-----------|-----------------------|------------------------|----------------|--------------------------|
| HWD [kg]  | 4.79E-06              | 1.06E-06               | 3.20E-07       | -1.66E-07                |
| NHWD [kg] | 3.66E+02              | 1.51E-02               | 1.00E+02       | -1.18E+01                |
| RWD [kg]  | 3.39E-02              | 4.03E-04               | 8.36E-04       | -1.31E-03                |
| CRU [kg]  | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |
| MFR [kg]  | 1.01E+02              | 9.00E+02               | 0.00E+00       | INA                      |
| MER [kg]  | 2.92E-01              | 0.00E+00               | 0.00E+00       | -1.84E-02                |
| EEE [MJ]  | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |
| EET [MJ]  | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |



#### Green Star

Table 7: Additional impact categories, 1 tonne of reinforcing bar

| Indicator                                 | Production<br>A1 – A3 | Waste processing<br>C3 | Disposal<br>C4 | Recycling potential<br>D |
|---|-----------------------|------------------------|----------------|--------------------------|
| HTPc [CTUh]                               | 4.89E-08              | 1.23E-10               | 2.11E-10       | -1.85E-09                |
| HTPnc [CTUh]                              | 8.18E-09              | 5.72E-12               | 5.71E-12       | 1.87E-10                 |
| LU [kg C deficit]                         | 2.18E+02              | 8.86E-01               | 4.70E-01       | 1.36E+00                 |
| RDW [m <sup>3</sup> H <sub>2</sub> O-eq.] | 3.45E+00              | 6.44E-03               | 6.27E-04       | -6.08E-02                |
| IR [kBq U235-eq.]                         | 3.50E+00              | 3.64E-02               | 1.19E-01       | -1.83E-01                |
| PM [kg PM2.5-eq.]                         | 7.22E-01              | 2.46E-03               | 9.02E-04       | -4.74E-02                |



### **Reinforcing Mesh**

#### **Product description**

Reinforcing mesh is produced in sheets by welding ribbed steel wires at right angles, creating gaps that are either square or rectangular. Meshes vary through both the diameter of the wire used and the spacing between longitudinal and cross wires. The size of mesh sheets can also be customised for particular applications (e.g. trenches) or to facilitate transport.

| Product          | Size range (mm)               | Section |
|------------------|-------------------------------|---------|
| Reinforcing Mesh | SL53 to SL81, RL718 to RL1218 |         |

#### Changes in results from previous EPD

GWP, ADPF, AP, EP and ADPE have decreased significantly due to an increased proportion of production from EAF and EAF efficiency improvements. POCP impacts have increased slightly due to increases in carbon monoxide, nitrogen oxides and sulphur dioxide emissions at Whyalla BOS. ODP has decreased by three orders of magnitude, due to updates in the background data sets reflecting the phase out of ozone depleting substances.

### **Results of assessment**

#### **Environmental impact indicators**

The following indicators describe potential environmental impacts for each product per declared unit.

| Indicator                                     | Production<br>A1 – A3 | Waste processing<br>C3 | Disposal<br>C4 | Recycling potential<br>D |
|---|-----------------------|------------------------|----------------|--------------------------|
| GWP [kg CO <sub>2</sub> -eq.]                 | 2.06E+03              | 2.60E+00               | 4.51E+00       | -5.21E+02                |
| ODP [kg CFC11-eq.]                            | 2.22E-12              | 1.51E-14               | 1.46E-14       | -1.21E-13                |
| AP [kg SO <sub>2</sub> -eq.]                  | 5.78E+00              | 1.72E-02               | 1.27E-02       | -4.66E-01                |
| EP [kg PO <sub>4</sub> <sup>3-</sup> -eq.]    | 6.44E-01              | 4.22E-03               | 1.35E-03       | -8.21E-02                |
| POCP* [kg C <sub>2</sub> H <sub>4</sub> -eq.] | 1.46E+00              | 1.89E-03               | 1.18E-03       | -6.18E-01                |
| ADPE [kg Sb-eq.]                              | 6.22E-04              | 2.93E-06               | 3.39E-07       | -2.28E-04                |
| ADPF [MJ]                                     | 2.27E+04              | 4.92E+01               | 6.85E+01       | -5.33E+03                |

#### Table 8: Potential environmental impacts, 1 tonne of reinforcing mesh

The results from the impact assessment are only relative statements which give no information about the endpoint of the impact categories, exceeding of threshold values, safety margins or risk.

\*POCP values are slightly reduced due to nitrogen monoxide (NO) having a negative characterisation factor in the CML-IA methodology (Guinée et. al., 2002) implemented within EN 15804:2012+A1:2013. It should not be interpreted as NO reducing summer smog. This dampening effect present because the GaBi Databases used in this project (Sphera, 2020) split NO<sub>x</sub> emissions into NO and NO<sub>2</sub> for both mobile and stationary fuel combustion. POCP would be slightly higher if these emissions were instead grouped together as NO<sub>x</sub>. Extra care should be taken when comparing POCP values between EPDs.



#### **Resource indicators**

The following indicators describe the use of renewable and non-renewable material resources, renewable and non-renewable primary energy and water.

| Indicator            | Production<br>A1 – A3 | Waste processing<br>C3 | Disposal<br>C4 | Recycling potential<br>D |
|----------------------|-----------------------|------------------------|----------------|--------------------------|
| PERE [MJ]            | 1.24E+03              | 4.22E+00               | 4.94E+00       | -1.75E+02                |
| PERM [MJ]            | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |
| PERT [MJ]            | 1.24E+03              | 4.22E+00               | 4.94E+00       | -1.75E+02                |
| PENRE [MJ]           | 2.28E+04              | 5.02E+01               | 7.06E+01       | -5.36E+03                |
| PENRM [MJ]           | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |
| PENRT [MJ]           | 2.28E+04              | 5.02E+01               | 7.06E+01       | -5.36E+03                |
| SM [kg]              | 7.57E+02              | 0.00E+00               | 0.00E+00       | INA                      |
| RSF [MJ]             | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |
| NRSF [MJ]            | 4.91E+01              | 0.00E+00               | 0.00E+00       | 1.84E+01                 |
| FW [m <sup>3</sup> ] | 7.74E+00              | 1.31E-02               | 9.43E-04       | -6.02E-01                |

#### Table 9: Resource use, 1 tonne of reinforcing mesh

#### Wastes and other outputs

Table 10: Waste categories, 1 tonne of reinforcing mesh

| Indicator | Production<br>A1 – A3 | Waste processing<br>C3 | Disposal<br>C4 | Recycling potential<br>D |
|-----------|-----------------------|------------------------|----------------|--------------------------|
| HWD [kg]  | 5.54E-06              | 1.06E-06               | 3.20E-07       | -1.08E-06                |
| NHWD [kg] | 4.46E+02              | 1.51E-02               | 1.00E+02       | -7.66E+01                |
| RWD [kg]  | 4.02E-02              | 4.03E-04               | 8.36E-04       | -8.56E-03                |
| CRU [kg]  | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |
| MFR [kg]  | 7.52E+01              | 9.00E+02               | 0.00E+00       | INA                      |
| MER [kg]  | 5.02E-01              | 0.00E+00               | 0.00E+00       | -1.20E-01                |
| EEE [MJ]  | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |
| EET [MJ]  | 0.00E+00              | 0.00E+00               | 0.00E+00       | 0.00E+00                 |

#### Green Star

Table 11: Additional impact categories, 1 tonne of reinforcing mesh

| Indicator                                 | Production<br>A1 – A3 | Waste processing<br>C3 | Disposal<br>C4 | Recycling potential<br>D |
|---|-----------------------|------------------------|----------------|--------------------------|
| HTPc [CTUh]                               | 5.89E-08              | 1.23E-10               | 2.11E-10       | -1.20E-08                |
| HTPnc [CTUh]                              | 7.07E-09              | 5.72E-12               | 5.71E-12       | 1.22E-09                 |
| LU [kg C deficit]                         | 2.55E+02              | 8.86E-01               | 4.70E-01       | 8.86E+00                 |
| RDW [m <sup>3</sup> H <sub>2</sub> O-eq.] | 3.64E+00              | 6.44E-03               | 6.27E-04       | -3.96E-01                |
| IR [kBq U235-eq.]                         | 4.42E+00              | 3.64E-02               | 1.19E-01       | -1.19E+00                |
| PM [kg PM2.5-eq.]                         | 1.00E+00              | 2.46E-03               | 9.02E-04       | -3.09E-01                |



### Acronyms

| ADPE   | Abiotic Depletion Potential For Non-Fossil Resources   |
|--------|--|
| ADPF   | Abiotic Depletion Potential For Fossil Resources   |
| AP     | Acidification Potential  |
| AusLCI | Australian Life Cycle Inventory Database   |
| BF     | Blast Furnace  |
| BOS    | Basic Oxygen Steelmaking   |
| CML    | Centre Of Environmental Science At Leiden  |
| CRU    | Components For Reuse   |
| CTUh   | Comparative Toxic Unit (human toxic potential)   |
| EAF    | Electric Arc Furnace   |
| EEE    | Exported Electrical Energy   |
| EET    | Exported Thermal Energy  |
| EP     | Eutrophication Potential   |
| EPD    | Environmental Product Declaration  |
| FW     | Net Use Of Fresh Water   |
| Gabi   | Ganzheitliche Bilanzierung (German For Holistic Balancing)   |
| GWP    | Global Warming Potential   |
| HTPc   | Human Toxicity Potential, Cancer Effects   |
| HTPnc  | Human Toxicity Potential, Non-Cancer Effects   |
| HWD    | Hazardous Waste Disposed   |
| INA    | Indicator Not Assessed. A result marked with 'INA' indicates this is unable to be assessed using the worldsteel data set for scrap |
| IR     | Ionising Radiation   |
| ISO    | International Organization For Standardization   |
| LCA    | Life Cycle Assessment  |
| LCI    | Life Cycle Inventory   |
| LU     | Land Use   |
| MCI    | Material Circularity Indicator   |
| MER    | Materials For Energy Recovery  |
| MFR    | Materials For Recycling  |
| NHWD   | Non-Hazardous Waste Disposed   |
| NPI    | National Pollutant Inventory   |
| NRSF   | Use Of Non-Renewable Secondary Fuels   |
| ODP    | Ozone Depletion Potential  |
| PERE   | Use Of Renewable Primary Energy Excluding Renewable Primary Energy Resources Used As Raw Materials                                 |
| PERM   | Use Of Renewable Primary Energy Resources Used As Raw Materials  |
| PENRE  | Use Of Non-Renewable Primary Energy Excluding Non-Renewable Primary<br>Energy Resources Used As Raw Materials                      |
| PENRM  | Use Of Non-Renewable Primary Energy Resources Used As Raw Materials  |
| PENRT  | Total Use Of Non-Renewable Primary Energy Resources  |
| PERT   | Total Use Of Renewable Primary Energy Resources  |
| PM     | Particulate Matter   |
| POCP   | Photochemical Ozone Creation Potential   |
| RDW    | Resource Depletion - Water   |
| RSF    | Use Of Renewable Secondary Fuels   |
| RWD    | Radioactive Waste Disposed   |
| SM     | Use Of Secondary Material  |
| UN CPC | United Nations Central Product Classification  |



### References

- CEN. (2012). EN 15804:2012+A1:2013; Sustainability of construction works Environmental product declarations - Core rules for the product category of construction products. Brussels: European Committee for Standardization.
- Ellen McArthur Foundation. (2015) Circularity Indicators: An approach to measuring circularity. Available: https://www.ellenmacarthurfoundation.org/assets/downloads/insight/Circularity-Indicators\_ Project-Overview\_May2015.pdf
- EPD Australasia (2018). Instructions of the Australasian EPD Programme V3.0, 2018-09-18. Retrieved from https://epd-australasia.com/wp-content/uploads/2018/09/Australasian-Annex-to-GPI\_3.0-2018.pdf
- Frischknecht, R., Braunschweig, A., Hofstetter, P., & Suter, P. (2000). Human health damages due to ionising radiation in life cycle impact assessment. Environmental Impact Assessment Review (20), 159-189.
- Grant, T., Renouf, M. A., Sevenster, M., Ridoutt, B., Ximenes, F., Logie, J., . . . Lane, J. (2016). Best Practice Guide to Life Cycle Impact Assessment in Australia. Australian Life Cycle Assessment Society. Retrieved from www.alcas.asn.au
- Greco, S.L., Wilson, A.M., Spengler J.D., and Levy J.I. (2007). Spatial patterns of mobile source particulate matter emissions-to-exposure relationships across the United States. Atmospheric Environment (41), page 1011-1025.
- Green Building Council of Australia (2019). Green Star Design & As Built v1.3 Submission Guidelines. Retrieved from https://new.gbca.org.au/rate/rating-system/design-and-built/.
- Guinée, J. B., Gorrée, M., Heijungs, R., Huppes, G., Kleijn, R., de Koning, A., . . . Huijbregts, M. (2002). Handbook on life cycle assessment. Operational guide to the ISO standards. Dordrecht: Kluwer.
- IEPDS. (2019). PCR 2012:01, Construction products and Construction services, Version 2.31, 2019-12-20. The Internatinal EPD® System. Retrieved from http://www.environdec.com/en/PCR/Detail/?Pcr=8098.
- ISO (2006). ISO 14025:2006; Environmental labels and declarations Type III environmental declarations — Principles and procedures. Geneva: International Organization for Standardization.
- Milà i Canals, L., Romanyà, J., & Cowell, S. J. (2006). Method for assessing impacts on life support functions (LSF) related to the use of 'fertile land' in Life Cycle Assessment (LCA). Journal of Cleaner Production, 15, 1426-1440.
- Pickin, J., Randell, P., Trinh, J., & Grant, B. (2018). National Waste Report 2018. Australia: Department of the Environment and Energy.
- Rabi, A. and Spadaro, J.V. (2004). The RiskPoll software, version is 1.051 (dated August 2004). www.arirabl.com.
- Ridoutt, B. G., & Pfister, S. (2012). A new water footprint calculation method integrating consumptive and degradative water use into a single stand-alone weighted indicator; in Int J Life Cycle Assess (Received: 29 February 2012; Accepted: 8 June 2012 ed.). Springer-Verlag.
- Rosenbaum, R. K., Bachmann, T. M., Swirsky Gold, L., Huijbregts, M., Jolliet, O., Juraske, R., . . . Hauschild, M. Z. (2008). USEtox—the UNEP-SETAC toxicity model: recommended characterisation factors for human toxicity and freshwater ecotoxicity in life cycle impact assessment. Int J Life Cycle Assess, 13(7), 532–546.
- Sphera (2020); GaBi Databases 2020. http://www.gabi-software.com/support/gabi/gabi-database-2020-lcidocumentation/.
- Standards Australia (2019). AS/NZS 4671, Steel for the reinforcement of concrete. SAI Global.
- thinkstep-anz (2020); InfraBuild EPD Background Report v1.0. 24/08/2020.



### Notes

S-P-00858 Version 1.2

**REINFORCING BAR AND MESH** 



The Australian Steel (Operations) Company Pty Limited. For further information contact Australian Reinforcing Company.

158 Fitzgerald Rd, Laverton North VIC 3026 131 557

marketing@arcreo.com.au www.arcreo.com.au

**ARC - The Australian Reinforcing Company** Reinforcing the foundations of Australia since 1920